

TK-5201

BURNISH BLOCK SEALER

Color	CLEAR	
Packaging	METAL 5 GALLON PAILS, 55 GALLON LINED DRUMS	
Vehicle Type	METHACRYLATED ACRYLIC	
Solvent Type	MEK/TOLUENE	
Gloss at 60° angle	80 MINIMUM	
% Solids by Weight	28%	
Viscosity at 77° F	22 SECONDS ZAHN CUP #2	
Desired Dry Film	1.0 – 1.25 MILS	
Recommended Coverage Rate*	350 – 400 SQUARE FEET PER GALLON	
Average Dry Time at 70° F	Tack Free	1 – 5 MINUTES
	Recoat	30 – 60 MINUTES
	Full Cure	1 – 2 HOURS
Catalyst	N/A	
Thinner	DO NOT THIN	
Mix Ratio	N/A	
Pot Life	N/A	
Recommended Primer	Steel	N/A
	Galvanized	N/A
	Concrete	N/A
Flash Point	40 DEGREES F	
V.O.C.	674 GRAMS PER LITER	
A.I.M. Category V.O.C. Limit	NOT REGULATED WHEN APPLIED IN PLANT	

*Coverage: Theoretical coverage rates are a laboratory calculation based on the solids content and the desired dry film thickness. It does not take into consideration substrate porosity, application procedures, weather conditions, over-spray and wind loss.

05/09/02

It is always advisable to apply a test panel or mock up prior to the project start up. This will help to determine proper coverage, appearance and equipment requirements.

General Description:

TK-5201 IS A FAST DRY METHACRYLATED CLEAR ACRYLIC SEALER DESIGNED FOR IN PLANT COATING OF BURNISHED BLOCK. IT FORMS A GLOSSY FILM AND ENHANCES COLOR WITH A "WET LOOK". TK-5201 DRIES RAPIDLY SO THAT BLOCKS CAN BE STACKED AND CUBED SHORTLY AFTER COATING, SPEEDING PRODUCTION TIMES.

Resistance to:

Abrasion	EXCELLENT
Acid	EXCELLENT
Alkali	EXCELLENT
Humidity	EXCELLENT
Petroleum Products	GOOD
Salt Spray	EXCELLENT
Weather	EXCELLENT

Mixing Detail:

PRODUCT IS SUPPLIED READY TO USE. NO MIXING IS NECESSARY.

Surface Preparation:

SURFACE MUST BE CLEAN AND DRY. GRINDING DUSTS SHOULD BE REMOVED BY BRUSHING OR AIR BRUSH. WET GRINDERS SHOULD AIR BRUSH EXCESS WATER FROM SURFACE AND DRY TO THE POINT THAT THE SURFACE HAS LIGHTENED TO HELP ENHANCE THE "WET LOOK".

Application Procedure:

APPLY IN LINE WITH CONVENTIONAL OR AIRLESS SPRAY. APPLY EVENLY IN A UNIFORM MANNER TO YIELD UNIFORM APPEARING BLOCKS.

Clean Up:

CLEAN EQUIPMENT AND SPILLS WITH XYLENE.

Safety Information:

CONTAINS ORGANIC SOLVENTS WHICH HAVE HEALTH AND FIRE HAZARDS. AVOID BREATHING VAPORS AND OVERSPRAY MISTS. ALWAYS WEAR APPROPRIATE PERSONAL PROTECTIVE EQUIPMENT. GROUND ALL CONTAINERS AND SPRAY EQUIPMENT. DISPOSE OF EMPTY CONTAINERS IN ACCORDANCE TO ALL APPLICABLE REGULATIONS. SEE THIS PRODUCTS MSDS FOR FURTHER INFORMATION.

FIRST AID:

INHALATION: REMOVE FROM EXPOSURE TO FRESH AIR, TREAT SYMPTOMATICALLY, CALL A PHYSICIAN.

EYE CONTACT: IMMEDIATELY IRRIGATE WITH WATER FOR AT LEAST 15 MINUTES; GET MEDICAL ATTENTION.

SKIN CONTACT: WIPE OFF MATERIAL AND WASH THOROUGHLY WITH SOAP AND WATER.

INGESTION: DRINK 1 OR 2 GLASSES OF WATER TO DILUTE. DO NOT INDUCE VOMITING - GET MEDICAL ATTENTION.

HMIS:

HEALTH	2*
FLAMMABILITY	3
REACTIVITY	0
PERSONAL PROTECTION	I

Conditions Of Sale:

The TK Products Corp. warrants that this product conforms to label descriptions, is free from manufacturing defects and is fit for the ordinary purposes for which such goods are used. Inasmuch as the use of this product by others and factors affecting product performance are beyond TK Product's control, TK Products does not guarantee the results to be obtained. SHOULD THIS PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT OR, AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF THIS PRODUCT TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN THE CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.