



Division of Sierra Corporation
ISO 9001:2008 Certified

TK-HYDROMAX 2002 FOUNDATION WATERPROOF COATING

Solvent Base (Commercial) Meets ICC - AC 29
Division 7: Section 071416 - Cold Fluid Applied Waterproofing

TK-HYDROMAX 2002
Foundation Waterproof Coating

3 PRODUCTS



1. PRODUCT NAME

TK-HydroMax 2002 Foundation
Waterproof Coating

2. MANUFACTURER

TK PRODUCTS
DIVISION OF SIERRA CORPORATION
11400 West 47th Street
Minnetonka, MN 55343
952-938-7223
952-938-8084 (FAX)
e-mail: tksales@tkproduct.com
Website: http://www.tkproduct.com

3. PRODUCT DESCRIPTION

TK-HydroMax 2002 Foundation Waterproof Coating is a rubberized polymer formulation intended to waterproof poured concrete, CMU and precast for below grade foundation walls. It can bridge small cracks up to 1/16", helping it to prevent the penetration of water and other chemicals through the wall.

This product complies with the ICCAC29 (Acceptance Criteria for Cold, Liquid-Applied Below Grade, Exterior Damp proofing and Waterproofing Materials.)

4. TECHNICAL DATA

TK-2002 is a single component fluid applied foundation coating that is non-breathable.

Composition and Materials:

Rubberized polymer blend in an aromatic hydrocarbon blend solvent.

Non-Volatile Content:	48-50%
Color:	Pearl Gray
Flash Point:	Flammable, less than 76°F
Drying Time:	
Tack Free:	1 hour (recoat 2-4 hours)
Full Cure:	3-7 days

Applicable Standards

TK-HydroMax 2002 Foundation Waterproof Coating meets or exceeds the following standards:

- ASTM C1306/D5385, Hydrostatic Pressure Over Cracks
- ASTM C836-03 Section 6.10, Adhesion Strength
- ASTM D2939, Resistance to Water
- ASTM C836-89 Section 6.7, Low Temperature Flexibility and Crack Bridging

-ASTM C836-89, Film Thickness Vertical Surface

-ASTM C836-89 Section 6.12, Extensibility After Heat Aging, minimum

-ASTM E154-88 Section 13, Resistance to Decay

-ASTM E96-80, Water Vapor Permeance, water method

- VOC Content: Less than 600 grams per liter.

- A.I.M. Category: Waterproofing Sealer and Treatment - maximum VOC 600g/l.

- A.I.M. Definition: A coating formulated and recommended for application to a porous substrate for the primary purpose of preventing the penetration of water.

5. APPLICATION PROCEDURES AND INSTRUCTIONS

Preparation:

Material is ready for use and requires no mixing, unless signs of separation are observed. It is unlawful to further reduce with non-exempt solvents.

A clean, dry surface is required. Surface should be smooth and free of voids, spalled areas, loose substrate, protrusions, coarse aggregate and frost. Any dirt, oil, grease, debris or other contaminants must be removed. Defects in the surface, such as spalled or poorly joined areas must be repaired. New concrete should be allowed to cure until the surface appears dry. Concrete block laid and walls poured late in the year should be allowed to gain sufficient strength for good adhesion. All masonry joints need to be tooled and brushed. Assembly wall is to be unparged. All previous coatings must be removed.

Concrete

Any tie-holes, bugholes, surface abnormalities or voids that are larger than 1/2" in diameter, or more than 1/8" deep, or both, should either be pretreated with TK-2002 or repaired with a lean concrete mix of grout. Refer to ASTM D5295, Preparation of Concrete Surfaces for Adhered Membrane Waterproofing Systems, for more detail regarding substrate penetration.

Surfaces that are cracked, pitted, honeycombed or heavily bugholed can be filled by spraying 10-12" from the substrate. Note, however, that a higher amount of material will be consumed by utilizing this method; therefore it may be more efficient to fill the surface with a parge coat of lean mortar mix before application of TK-

2002. Such gaps may also be filled with a compatible sealant or caulk.

Remove windows, protrusions and form match lines. Also remove high spots that are greater than 1/32" in height.

To remove dirt, dust or loose stones, the substrate must be wire-brushed, swept with a stiff broom or blown with low pressure air. Surfaces of poor quality and with excessive laitance may require shotblasting or pressure washing to rid it of contaminants and provide a dense, smooth surface.

Application to "Green" Concrete or Damp Surfaces

TK-2002 may be applied to "green" (minimum of 3 days) concrete or over damp surfaces. Remove any visible or standing water prior to application.

Do not apply TK-2002 waterproofing membranes in wet weather. Once applied, the membranes will not be affected by light rain showers.

Control joints are to be filled and sprayed with TK-2002. Once cured, apply a bituthane sheet membrane that extends 1.5 foot on both sides of control joint.

Detailing:

Inside and Outside Corners

Apply a double coat of TK-2002 membrane starting in the corner and extending 6" for each side of the corner.

Drains and Penetrations

Once the waterproofing membrane has cured, penetration openings must be sealed and stabilized. Once sealed and stabilized, install a 1" fillet of a non-shrink butyl caulk around the protrusion. Install a bituthane membrane around the protrusion. Extend the membrane 6" onto the structural substrate and at least 2" onto the penetration.

Application:

A typical sprayer is a Graco 733/833 45:1 airless with a 0.037 tip. Brush and/or roller will also work for touchup and small applications.

Application of Drainage, Protection or Insulation

Protect TK-2002 membranes from other traffic, construction materials and backfill to avoid damage. Once the membrane has properly cured, use a protection/drainage composite with filter fabric. Be careful not to damage the TK-2002 membrane.



3 PRODUCTS

TK-HYDROMAX 2002
Foundation Waterproof Coating

Extruded polystyrene insulation boards also can be used and are compatible with TK-2002 membranes. Allow product to properly cure before installing extruded insulation board.

Coverage:

Coverage rate is inversely affected by the texture and porosity of the substrate. One coat is sufficient applied, 27 sq. ft. per gallon, or 50 wet mil film. This will give a dry film of 20 dry mils. Inspect the surface for continuous and uninterrupted coating. Any area that is thin may be recoated.

Backfill:

Backfill should not contain sharp rock or aggregate over 2" in diameter. Backfill in small loads or lifts.

Limitations:

TK-HydroMax 2002 Foundation Waterproof Coating can be applied at temperatures of 0° F - 100° F. Apply TK-2002 directly to structural surfaces. Do not apply TK-2002 membranes over lightweight insulating concrete. Insulation, if used, must be installed over the membrane. Do not apply TK-2002 on foundation walls that are more than 30 feet deep without prior approval from TK Products.

Cleanup of Equipment:

Use TK-00 Solvent. For sprayer, pump the solvent through the spray equipment to remove residue of materials which can clog the hose and wand assembly.

Precautions:

TK-HydroMax 2002 Foundation Waterproof Coating contains aromatic hydrocarbon. Keep away from heat and flame. Prevent buildup of vapors. Use only with adequate ventilation. Do not inhale vapor or spray mist. If you experience eye watering, headaches or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, increase fresh air entry or wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after the application processes. Any person using a respirator must be trained on proper respirator use. Close container after each use. Avoid contact with eyes, skin, and clothing. Wash after handling. KEEP OUT OF REACH OF CHILDREN. Do not allow vapors to penetrate into foodstuffs. TK-HydroMax 2002 Foundation Waterproof Coating is not toxic in its cured state.

First Aid:

If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately. For contact with skin, wash thoroughly with soap and water. If swallowed, do not induce vomiting. Call a physician immediately.

In Case of Fire:

Use foam, CO2, dry chemical. Do not use water spray. Generic Name: Petroleum Distillates.

Spills or Leaks:

Contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused content in accordance with local, state and federal regulations. For safety controls, Material Safety Data Sheets are available from TK Distributors, the TK Office or the TK Website. This information should be read before using this product.

6. AVAILABILITY

TK-HydroMax 2002 Foundation Waterproof Coating is available through TK Distributors. Contact TK Products for the nearest distributor. Packaged in: 55-gallon drums, and 5-gallon pails.

Maintenance

Minimal maintenance is required. If weathering occurs to the exposed area, TK-2002 can be reapplied to the affected area.

7. CONDITIONS OF SALE/ LIMITED WARRANTY5 YEAR MATERIAL WARRANTY UPON REQUEST

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS

WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

8. TECHNICAL SERVICES

The TK office offers assistance with specifications, performance test data and field services.

9. FILING SYSTEMS

Information Handling Services
PO Box 1213
Englewood, CO 80150
Information Marketing Services
13271 Northend
Oak Park, MI 48237

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

FOR INDUSTRIAL USE ONLY

12/09

Applicable Standards	TK-HydroMax 2002 Performance
ASTM C1306/D5385 - Hydrostatic Pressure Over Cracks	.310 (45.0)
ASTM C836-03 Section 6.10 - Adhesion Strength	11.9 lbf/inch
ASTM D2939 - Resistance to Water	Passed
ASTM C836-89 Section 6.7 - Low Temperature Flexibility and Crack Bridging	11.9 lbf/inch
ASTM E96-80 - Water Vapor Permeance, Method B	0.09 Perms 0.0015 Permeability